


HessLite™ LIGHTWEIGHT BLENDED MATERIALS MAC™ Mortar POINTING

HESSLITE™ MAC™ POINTING MORTARS



1 | **PRODUCTS:** HessLite™ MAC™ Pointing Mortar

2 | **MANUFACTURER:** Hess Performance Products, 100 Hess Drive, Malad, Idaho 83252

Product Availability & Support: 208.766.4777 x142 -
salesteam@hesspumice.com

Website: hesslite.com

3 | **PRODUCT DESCRIPTIONS:** HessLite MAC Pointing Mortar is a lightweight pointing mortar for grouting applications with joints GREATER than 3/8".

HessLite MAC Fine Pointing Mortar is an extra-lightweight, fine-aggregate pointing mortar for grouting applications with joints LESS than 1/2".

HessLite MAC Pointing Mortars have excellent flow through a grout bag. These pointing mortars include efflorescence reducing additives and provide great bond strengths, low shrinkage, and excellent workability. Contain a blend of Portland Cement, graded lightweight aggregate, hydrated lime, and proprietary additives—an ideal complimentary performance mortar for lightweight masonry products.

Specifications: Meets the property specifications of ASTM C270.

Uses: HessLite MAC Pointing Mortars are formulated for grouting natural stone, manufactured stone, and thin-brick veneers. HessLite MAC Pointing Mortars can also be used to repair and repoint grout joints in block and brick. Available in a variety of colors to meet individual job requirements.

Advantages: HessLite MAC Pointing Mortars have the following advantages:

- Lightweight for easy handling and reduced structural loading.
- High bond and compressive strengths. ▪ Excellent workability and board life.
- Low shrinkage, high water retention. ▪ Crack-resistant.
- Pre-blended color and uniformity. ▪ Includes efflorescence-reducing additives.

Colors: HessLite MAC Pointing Mortars may be ordered in standard colors and special order colors. The efflorescence control and water repellent properties help the long term appearance of colored mortar. For color consistency use the same water and tooling techniques. Color can vary dramatically. Test installation techniques prior to application.

Packaging: HessLite MAC Pointing Mortars are available in moisture-resistant bags.

Coverage: One 50 lb. bag will yield approximately 0.58 cu.ft. Coverage will vary due to application thickness and waste.

Shelf Life: When stored in a cool dry area, with low humidity, shelf life is approximately six months to one year.

Efflorescence: HessLite MAC Mortars have proven experience reducing efflorescence, however, due to variables beyond our control, we cannot guarantee efflorescence will not occur.

Suitable Substrates: All substrates must be clean and free from any dirt, oil, paint, bond breakers or any substances which may hinder bond. The substrate must be structurally sound and conform



Product Data Sheets are subject to change without notification. Test results shown are typical but field performance will vary depending on installation methods and job conditions. HessLite, BondMate, and PolyThin are trademarks of Hess Performance Products. MAC and VBM are trademarks of R-Crete Inc.

HESSLITE INSTALLATION SYSTEM PRODUCT CROSS REFERENCES

- For laying up natural stone, brick, and CMUs with a grout joint, we recommend using HessLite Type-S Mortar.
- HessLite MAC Pointing Mortars are a great choice for grouting masonry veneers and pavers bonded with VBM BondMate (Medium Bed applications) and VBM PolyThin (Thinbed applications) mortars.

HessLite[™] LIGHTWEIGHT BLENDED MATERIALS MAC[™] Mortar POINTING

to good engineering practices—meeting building code requirements. Movement in the substrate can cause cracking in the finished mortar and bond failure. All expansion or movement joints shall be brought through the mortar to the surface.

Limitations: Do not apply when temperatures are below 40° F prior to cure. Do not add any admixtures without prior consent. Follow ASTM and ANSI guidelines for installation in high heat, cold or wind. Color may change due to differing water content, weather, absorption, and tooling techniques. Do Not Over Mix (3-5 min), as high air content will lower strength. Substrate must be sound—any cracks or excessive movement may telegraph through mortar or cause bond failure. Proper design and application procedures must be followed.

4 | **TECHNICAL DATA:** MAC Pointing Mortars meet the property specifications of ASTM C270 Type-S (>1800 psi). The mortar consists of Portland Cement (ASTM C150), Type-S Lime (ASTM C207), R-Mortar Aid, J-4 R-Repel Aid integral water repellent, and graded lightweight aggregate. Compressive strength specimen must be air cured per ANSI 118.1 due to high water retention and water repellency. Water content of approximately 30%.

5 | INSTALLATION

Mixing Instructions: Proper mixing is critical for performance and workability. Start with six (6) quarts of clean water, add entire bag of MAC Pointing Mortar and mix at LOW SPEED for **3–5 minutes**. DO NOT OVER MIX! Mixing should be done carefully to minimize air entrainment, as high air content will reduce performance. **Allow to slake for 7 to 10 minutes.** (Lightweight aggregate will continue to absorb water.) Gently re-mix and adjust consistency with additional water if necessary.

Application: Use a trowel or grout bag to place pointing mortar. Allow placed mortar to become thumbprint-hard before pressing into joint and finishing joint with a trowel, rake, brush, or jointing tool as desired. Follow IBC, CBC, ASTM and local building codes for installation and curing requirements. It is the responsibility of the user to insure the mortar is suitable for the intended application, that the substrate is properly prepared and application is performed correctly.

System: HessLite MAC Pointing Mortars are part of the **HessLite Installation System**. Visit www.HessLite.com for complete lightweight product line.

6 | **AVAILABILITY AND COST:** HessLite MAC Pointing Mortars are available from select distributors. For distributor information, contact Jason at **208.766.4777 x142** or salesteam@hesspumice.com

7 | **WARRANTY:** The technical information and usage statements are based on our best knowledge. The contents of this specification sheet are presented for informational purposes only and do not constitute responsibility for their use. The manufacturer will replace only that material which is proven defective due to quality of the components or the manufacturing process.



CAUTION: Prolonged exposure to dust may cause delayed lung disease. Eliminate exposure to dust. Use NIOSH approved mask for silica dust. Freshly mixed materials may cause skin irritation. Avoid direct contact where possible and wash exposed skin areas promptly. If any cementitious materials get into the eyes, rinse immediately and repeatedly with water and get prompt medical attention. See SDS sheet.

NOTICE: Testing for crystalline silica (airborne particles of respirable size) has shown no measurable rates (<0.1%) of Crystalline Silica (SiO₂) to be present in HessLite MAC Mortars.

WARNING: Products containing crystalline silica (airborne particles of respirable size) are known to the State of California to cause cancer. For more information go to www.p65Warnings.ca.gov.